Media One Data Sheet
Sunset™

Sunset™

Product Code	Construction	Material	Weight	Thickness	Max Width
TXJBB/TXCJBB	Warp-knit	100% Coated PES/FR	9.03 oz/sq.yd	0.44 mm	196 in.
TXJBB/TXCJBB-RY	Warp-knit	100% Recycled PES			
TXJBB/TXCJBB-T	Warp-knit	100% Uncoated PES			

Description
White Front Blackback Blockout Fabric

Features
Black-Backed Resin Coating, Durable, Tradeshow best seller

Applications
SEG Frames | Blockout | Displays | Exhibit Graphics

Ink Compatibility
Dye Sub Transfer | Dye Sub Direct| UV| Latex

Print Side
Sublimation | Outside

Shrink (l):	1.73%
Shrink (w):	0.47%
Stretch (l):	2.53%
Stretch (w):	4.80%
Stretch at Burst (l):	90.00%
Stretch at Burst (w):	130.00%
Burst Strength (l):	94 lbs/in.
Burst Strength (w):	178 lbs/in.
Tensile Strength (l):	5 lbs/in.
Tensile Strength (w):	9 lbs/in.
Burst Strength:	211 lbs
Yellowing:	1.06 dE
Max Roll Length:	100m
Available Recycled:	Yes
Available Anti-microbial:	Yes



All fabrics are NFPA-701 flame Retardant Certified
B1 M1 Certifications Available on Request.
Recommended transfer settings for sublimation are 374°F-190°C°F for 40 seconds at 40psi.

***Recycling of Coated PES**
Unlike most natural fibers, Coated PES products may be recycled. We know the technique from remelting PET-bottles to other Coated PES products.Textile products may also be turned into granules and remelted into new Coated PES products via a chemical process. Pure Coated PES textiles and some blends may be recycled with this technique. Colorant may be extracted before the product turns into granules and it will then be possible to dye the new Coated PES product.
The end-user is responsible for the disposal of recycled Coated PES.

www.mediaoneusa.com
11752 Markon Drive Garden Grove, CA 92841-1810
web@mediaoneusa.com | 833-435-5661

The information supplied in this technical sheet is for guidance only and should not be construed as a warranty. This document is not legally binding and is based on average results from current production. Purchaser is fully responsible for determining the product suitability for its intended application. Technical details are subject to change without prior notice. Please contact Media One Digital Imaging Solutions, LLC for any additional information you may require.